



SPECIFICATION

- · Supplier : Samsung electro-mechanics
- Product : Multi-layer Ceramic Capacitor
- · Samsung P/N :
- CL10A474KQ8NNNC

(Reference sheet)

- Description :
- CAP, 470nF, 6.3V, ±10%, X5R, 0603

A. Samsung Part Number

			<u>10</u> <u>A</u> ② ③	<u>474</u> <u>K</u> ④ ⑤	<mark>Q</mark> ©	<u>8</u> 7	<u>N</u> 8	<u>N</u> 9	<u>N</u> 10	<u>С</u> Ш	
1	Series	Samsung Multi-lay	yer Cera	mic Capaci	tor						
2	Size	0603 (inch cod	e)	L: 1.60) ± 0.10	mm			W:	$0.80\pm0.10 \text{ mm}$	
3	Dielectric	X5R		8	Inner	elect	rode			Ni	
4	Capacitance	470 nF			Termi	natio	n			Cu	
5	Capacitance	±10 %			Platin	g				Sn 100% (Pb Free)	
	tolerance			9	Produ	ıct				Normal	
6	Rated Voltage	6.3 V		10	Speci	al				Reserved for future use	
\bigcirc	Thickness	0.80 ± 0.10 mm		1	Packa	nging				Cardboard Type, 7" reel	

B. Structure & Dimension



Samsung P/N	Dimension(mm)						
Samsung F/N	L	W	Т	BW			
CL10A474KQ8NNNC	1.60 ± 0.10	0.80 ± 0.10	0.80 ± 0.10	0.30 ± 0.20			

C. Samsung Reliablility Test and Judgement Condition

Tan δ (DF) 0.05 max. treated at 150°C+0/-10°C for 1 hour and maintained ambient air for 24±2 hours. Insulation 10,000Mohm or 100Mohm×μ [±] Rated Voltage 60~120 sec. Appearance No abnormal exterior appearance Microscope (×10) Withstanding No dielectric breakdown or 250% of the rated voltage Voltage mechanical breakdown 250% Temperature XSR Characteristics (From-55°C to 85°C, Capacitance change should be within ±15%) Adhesive Strength Adhesive Strength No peeling shall be occur on the terminal electrode 500g·f, for 10±1 sec. Bending Strength Capacitance change : within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be solder d newly SAg3.0Cu0.5 solder Soldering Heat Tan δ, IR : initial spec. Yibration Test Capacitance change : within ±7.5% Soldering Heat Tan δ, IR : initial spec. Amplitude : 1.5mm Vibration Test Capacitance change : within ±12.5% Amplitude : 1.5mm Resistance Tan δ, IR : initial spec. Yibrin trad voltage Whichever is smaller Huth rated voltage High Temperature		Judgement	Test condition				
Tan δ (DF) 0.05 max. treated at 150°C+0/-10°C for 1 hour and maintained ambient air for 24±2 hours. Insulation 10.000Mohm or 100Mohm×μ ^E Rated Voltage 60~120 sec. Appearance No abnormal exterior appearance Microscope (×10) Withstanding No dielectric breakdown or 250% of the rated voltage Voltage mechanical breakdown 250% Temperature XSR Characteristics (From-55°C to 85°C, Capacitance change should be within ±15%) Adhesive Strength Adhesive Strength No peeling shall be occur on the terminal electrode 500g·f, for 10±1 sec. Bending Strength Capacitance change : within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be solder of newly Solder pot : 270±5°C, 10±1sec. Soldering Heat Tan δ, IR : initial spec. Yibration Test Capacitance change : within ±17.5% Soldering Heat Tan δ i. R : initial spec. Yibr hated voltage Vibration Test Capacitance change : within ±12.5% Amplitude : 1.5mm From 10Hz to 55Hz (return : fmin.) 2000K of the rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs IR : 5000Mohm or 25Mohm × μ ^E With rated volta	Capacitance	Within specified tolerance	1 ^{kHz} ±10% / 1.0±0.2Vrms				
Resistance Whichever is smaller Appearance No abnormal exterior appearance Microscope (×10) Withstanding No dielectric breakdown or mechanical breakdown 250% of the rated voltage Temperature X5R 250% of the rated voltage Characteristics (From-55°C to 85°C, Capacitance change should be within ±15%) Adhesive Strength No peeling shall be occur on the terminal electrode 500g-f, for 10±1 sec. Bending Strength Capacitance change : within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.) Resistance to Capacitance change : within ±7.5% Solder pot : 270±5°C, 10±1sec. Soldering Heat Tan 5, IR : initial spec. Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Moisture Capacitance change : within ±12.5% Tan 5 : 0.075 max With rated voltage 40±2°C, 90-95%RH, 500+12/-0hrs High Temperature Capacitance change : within ±12.5% Whichever is smaller With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs	Tan δ (DF)	0.05 max.	*A capacitor prior to measuring the capacitance is heat treated at $150^{\circ}C+0/-10^{\circ}C$ for 1 hour and maintained in ambient air for 24±2 hours.				
AppearanceNo abnormal exterior appearanceMicroscope (×10)WithstandingNo dielectric breakdown or mechanical breakdown250% of the rated voltageYoltagemechanical breakdown250% of the rated voltageTemperatureX5R Characteristics(From-55°C to 85°C, Capacitance change should be within ±15%)Adhesive StrengthNo peeling shall be occur on the terminal electrode500g·f, for 10±1 sec.Bending StrengthCapacitance change : utim ±12.5%Bending to the limit (1mm) with 1.0mm/sec.SolderabilityMore than 75% of terminal surface is to be soldered newlySnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.)Resistance to Vibration TestCapacitance change : Capacitance change : mital spec.Solder pot : 270±5°C, 10±1sec.Vibration Test ResistanceCapacitance change : mital spec.within ±12.5% Mombum or 25Mohm × μ^{F} Whichever is smallerAmplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : mital spec.With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrsHigh Temperature ResistanceCapacitance change : mital spelWith ±12.5% Max. operating temperature 1000+48/-0hrsHigh Temperature ResistanceCapacitance change : mital spelWith ±12.5% Max. operating temperature 1000+48/-0hrs	Insulation	10,000Mohm or 100Mohm× <i>μ</i> F	Rated Voltage 60~120 sec.				
Withstanding No dielectric breakdown or mechanical breakdown 250% of the rated voltage Temperature X5R Characteristics (From-55 °C to 85 °C, Capacitance change should be within ±15%) Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g ·f, for 10±1 sec. Bending Strength Capacitance change : within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.) Resistance to Capacitance change : within ±7.5% Solder pot : 270±5°C, 10±1sec. Soldering Heat Tan ō, IR : initial spec. Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Moisture Capacitance change : within ±12.5% Tan ō : 0.075 max IR : 500Mohm or 25Mohm × μ ^c Whichever is smaller With 200% of the rated voltage High Temperature Capacitance change : within ±12.5% Whichever is smaller With 200% of the rated voltage High Temperature Capacitance change : within ±12.5% Whichever is smaller With 200% of the rated voltage							
Voltagemechanical breakdownTemperature CharacteristicsX5R (From-55 °C to 85 °C, Capacitance change should be within $\pm 15\%$)Adhesive Strength of TerminationNo peeling shall be occur on the terminal electrode500g f, for 10±1 sec.Bending Strength of TerminationCapacitance change : within $\pm 12.5\%$ Bending to the limit (1mm) with 1.0mm/sec.SolderabilityMore than 75% of terminal surface is to be soldered newlySnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.)Resistance to Vibration TestCapacitance change : capacitance change : within $\pm 7.5\%$ Solder pot : $270\pm5°C$, $10\pm1sec$.Vibration TestCapacitance change : capacitance change : within $\pm 5\%$ Tan δ , IR : initial spec.Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : tan δ : 0.075 max IR : Soldem or 25Mohm × μ^{c} With 200% of the rated voltage Max. operating temperature 1000+48/-0hrsHigh Temperature ResistanceCapacitance change : to : 0.075 max IR : 1,000Mohm or 50Mohm × μ^{c} With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs	Appearance	No abnormal exterior appearance	Microscope (×10)				
Temperature CharacteristicsX5R (From-55°C to 85°C, Capacitance change should be within ±15%)Adhesive Strength of TerminationNo peeling shall be occur on the terminal electrode500g·f, for 10±1 sec.Bending StrengthCapacitance change : within ±12.5%Bending to the limit (1mm) with 1.0mm/sec.SolderabilityMore than 75% of terminal surface is to be soldered newlySnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.)Resistance to Soldering HeatCapacitance change : within ±7.5% Capacitance change : within ±7.5% Capacitance change : within ±5% Tan δ, IR : initial spec.Solder pot : 270±5°C, 10±1sec.Vibration Test ResistanceCapacitance change : within ±12.5% Tan δ, IR : initial spec.Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : within ±12.5% Whichever is smallerWith rated voltage Max. operating temperature IR : 1,000Mohm or 50Mohm × μ F Whichever is smallerWith 200% of the rated voltage Max. operating temperature 1000+48/-0hrs			250% of the rated voltage				
Characteristics(From-55°C to 85°C, Capacitance change should be within ±15%)Adhesive Strength of TerminationNo peeling shall be occur on the terminal electrode500g·f, for 10±1 sec.Bending StrengthCapacitance change : within ±12.5%Bending to the limit (1mm) with 1.0mm/sec.SolderabilityMore than 75% of terminal surface is to be soldered newlySnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.)Resistance to Soldering HeatCapacitance change : within ±7.5% Tan δ_i IR : initial spec.Solder pot : 270±5°C, 10±1sec.Vibration Test ResistanceCapacitance change : within ±5% Tan δ_i IR : initial spec.Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : within ±12.5% Tan δ_i 0.075 max IR : 500Mohm or 25Mohm × μ F Whichever is smallerWith 200% of the rated voltage Max. operating temperature IR : 1,000Mohm or 50Mohm × μ F Whichever is smaller	Voltage	mechanical breakdown					
Adhesive Strength of TerminationNo peeling shall be occur on the terminal electrode500g·f, for 10 ± 1 sec.Bending StrengthCapacitance change : within ±12.5%Within ±12.5%Bending to the limit (1mm) with 1.0mm/sec.SolderabilityMore than 75% of terminal surface is to be soldered newlySnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.)Resistance to Soldering HeatCapacitance change : Tan δ_i IR : initial spec.within ±7.5% Solder pot : 270±5°C, 10±1sec.Vibration TestCapacitance change : capacitance change : Tan δ_i IR : initial spec.Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : Tan δ_i : 0.075 max IR : Soldom or 25Mohm × μ^{c} Whichever is smallerWith 200% of the rated voltage Max. operating temperature 100+48/-0hrsHigh Temperature ResistanceCapacitance change : tan δ_i : 0.075 max IR : Michever is smallerWith 200% of the rated voltage Max. operating temperature 1000+48/-0hrs	Temperature	X5R					
of Terminationterminal electrodeBending StrengthCapacitance change :within $\pm 12.5\%$ Bending to the limit (1mm)With 1.0mm/sec.SolderabilityMore than 75% of terminal surface is to be soldered newlySnAg3.0Cu0.5 solder 245 \pm 5°C, 3 \pm 0.3sec. (preheating : 80~120°C for 10~30sec.)Resistance to Soldering HeatCapacitance change :within \pm 7.5% Solder pot : 270 \pm 5°C, 10 \pm 1sec.Vibration TestCapacitance change :within \pm 5% Tan δ , IR : initial spec.Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change :within \pm 12.5% Whichever is smallerWith rated voltage 40 \pm 2°C, 90~95%RH, 500+12/-0hrsHigh Temperature ResistanceCapacitance change :within \pm 12.5% Whichever is smallerWith 200% of the rated voltage Max. operating temperature 1000+48/-0hrs	Characteristics	(From-55℃ to 85℃, Capacitance change should be within ±15%)					
Bending StrengthCapacitance change :within $\pm 12.5\%$ Bending to the limit (1mm) with 1.0mm/sec.SolderabilityMore than 75% of terminal surface is to be soldered newlySnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.)Resistance to Soldering HeatCapacitance change :within $\pm 7.5\%$ Solder pot : 270±5°C, 10±1sec.Vibration TestCapacitance change :within $\pm 5\%$ Tan δ , IR : initial spec.Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change :within $\pm 12.5\%$ Tan δ :0.075 max IR :With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrsHigh Temperature ResistanceCapacitance change :within $\pm 12.5\%$ Whichever is smallerWith 200% of the rated voltage Max. operating temperature 1000+48/-0hrs	Adhesive Strength	No peeling shall be occur on the					
with 1.0mm/sec.SolderabilityMore than 75% of terminal surface is to be soldered newlySnAg3.0Cu0.5 solder $245\pm5^{\circ}$ C, 3 ± 0.3 sec. (preheating : $80 \times 120^{\circ}$ C for 10×30 sec.)Resistance to Soldering HeatCapacitance change : Tan δ , IR : initial spec.within $\pm 7.5\%$ Solder pot : $270\pm5^{\circ}$ C, 10 ± 1 sec.Vibration TestCapacitance change : Capacitance change : man δ , IR : initial spec.Amplitude : 1.5 mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : m δ : 0.075 max IR : S00Mohm or 25Mohm × μ^{f} Whichever is smallerWith 200% of the rated voltage Max. operating temperature 1000+48/-0hrsHigh Temperature ResistanceCapacitance change : m δ : 0.075 max IR : Michever is smallerWith $\pm 12.5\%$ Mith $\pm 12.5\%$ Whichever is smallerWith 200% of the rated voltage Max. operating temperature 1000+48/-0hrs	of Termination	terminal electrode					
SolderabilityMore than 75% of terminal surface is to be soldered newlySnAg3.0Cu0.5 solder $245\pm5^{\circ}$ C, 3 ± 0.3 sec. (preheating : $80\sim120^{\circ}$ C for $10\sim30$ sec.)Resistance to Soldering HeatCapacitance change : Tan δ , IR : initial spec.within $\pm7.5\%$ Solder pot : $270\pm5^{\circ}$ C, 10 ± 1 sec.Vibration TestCapacitance change : max, IR : initial spec.within $\pm5\%$ From 10Hz to 55 Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : Tan δ : 0.075 max IR : 500 Mohm or 25 Mohm × μ F Whichever is smallerWith 200% of the rated voltage Max. operating temperature Max. operating temperature IR : $1,000$ Mohm or 50 Mohm × μ F Whichever is smallerWith 200% of the rated voltage Max. operating temperature $100+48/-0$ hrs	Bending Strength	Capacitance change : within ±12.5%	Bending to the limit (1mm)				
is to be soldered newly $245\pm5^{\circ}C, 3\pm0.3sec.$ (preheating : $80\sim120^{\circ}C$ for $10\sim30sec.$)Resistance to Soldering HeatCapacitance change : Tan δ , IR : initial spec.within $\pm7.5\%$ Solder pot : $270\pm5^{\circ}C, 10\pm1sec.$ Vibration TestCapacitance change : Capacitance change : Tan δ , IR : initial spec.Amplitude : $1.5mm$ From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : Tan δ : 0.075 max IR : $500Mohm or 25Mohm × \mu^{f}$ Whichever is smallerWith 200% of the rated voltage Max. operating temperature $100+48/-0hrs$ High Temperature ResistanceCapacitance change : N : 0.075 max IR : $1,000Mohm or 50Mohm × \mu^{f}$ Whichever is smallerWith 200% of the rated voltage Max. operating temperature $100+48/-0hrs$			with 1.0mm/sec.				
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder				
Resistance to Soldering HeatCapacitance change : Tan δ , IR : initial spec.within $\pm 7.5\%$ Solder pot : $270\pm5^{\circ}$ C, 10 ± 1 sec.Vibration TestCapacitance change : Tan δ , IR : initial spec.Within $\pm 5\%$ Tan δ , IR : initial spec.Amplitude : 1.5 mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : Tan δ : 0.075 max IR : 500 Mohm or 25Mohm × μ F Whichever is smallerWith rated voltage $40\pm2^{\circ}$ C, $90\sim95\%$ RH, $500+12/-0$ hrsHigh Temperature ResistanceCapacitance change : 10.075 max IR : $1,000$ Mohm or 50Mohm × μ F Whichever is smallerWith 200% of the rated voltage Max. operating temperature $1000+48/-0$ hrs		is to be soldered newly	245±5℃, 3±0.3sec.				
Soldering HeatTan δ , IR : initial spec.Vibration TestCapacitance change : Tan δ , IR : initial spec.within $\pm 5\%$ From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : Tan δ : 0.075 maxwithin $\pm 12.5\%$ μ^{F} Whichever is smallerMuith rated voltage $40\pm 2^{\circ}$ C, 90~95%RH, 500+12/-0hrsHigh Temperature ResistanceCapacitance change : within $\pm 12.5\%$ $IR : 500Mohm or 25Mohm × \mu^{F}Whichever is smallerWith 200\% of the rated voltageMax. operating temperature1000+48/-0hrs$			(preheating : 80~120℃ for 10~30sec.)				
Vibration TestCapacitance change : Tan δ , IR : initial spec.within $\pm 5\%$ From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : Tan δ :within $\pm 12.5\%$ Tan δ :Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : within $\pm 12.5\%$ Whichever is smallerWith rated voltage $40\pm 2^{\circ}$ C, 90~95%RH, 500+12/-0hrsHigh Temperature ResistanceCapacitance change : within $\pm 12.5\%$ Tan δ : 0.075 max IR : $1,000$ Mohm or 25Mohm × μ F Whichever is smallerWith 200% of the rated voltage Max. operating temperature $1000+48/-0hrs$	Resistance to	Capacitance change : within ±7.5%	Solder pot : 270±5°C, 10±1sec.				
Tan δ , IR : initial spec.From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)Moisture ResistanceCapacitance change : within ±12.5% Tan δ : 0.075 max IR : 500Mohm or 25Mohm × μ F Whichever is smallerWith rated voltage 40±2°C, 90~95%RH, 500+12/-0hrsHigh Temperature ResistanceCapacitance change : within ±12.5% Tan δ : 0.075 max IR : 1,000Mohm or 50Mohm × μ F Whichever is smallerWith 200% of the rated voltage Max. operating temperature 1000+48/-0hrs	Soldering Heat						
ResistanceTan δ :0.075 max $40\pm 2^{\circ}\mathbb{C}$, 90~95%RH, 500+12/-0hrsIR:500Mohm or 25Mohm × μ^{F} Whichever is smaller $40\pm 2^{\circ}\mathbb{C}$, 90~95%RH, 500+12/-0hrsHigh Temperature ResistanceCapacitance change :within $\pm 12.5\%$ Tan δ :With 200% of the rated voltage Max. operating temperature 1000+48/-0hrsIR:1,000Mohm or 50Mohm × μ^{F} Whichever is smaller $1000+48/-0hrs$	Vibration Test	i e	From 10Hz to 55Hz (return : 1min.)				
ResistanceTan δ :0.075 max $40\pm 2^{\circ}\mathbb{C}$, 90~95%RH, 500+12/-0hrsIR:500Mohm or 25Mohm × μ^{F} Whichever is smaller $40\pm 2^{\circ}\mathbb{C}$, 90~95%RH, 500+12/-0hrsHigh Temperature ResistanceCapacitance change :within $\pm 12.5\%$ Tan δ :With 200% of the rated voltage Max. operating temperature 1000+48/-0hrsIR:1,000Mohm or 50Mohm × μ^{F} Whichever is smaller $1000+48/-0hrs$	Moisture	Capacitance change : within ±12.5%					
Whichever is smaller High Temperature Resistance IR : 1,000Mohm or 50Mohm × μF Whichever is smaller	Resistance	Tan δ : 0.075 max	40±2℃, 90~95%RH, 500+12/-0hrs				
High Temperature ResistanceCapacitance change : 0.075 max IR : Whichever is smallerwithin $\pm 12.5\%$ Max. operating temperature 1000+48/-0hrsWith 200% of the rated voltage Max. operating temperature 1000+48/-0hrs		IR : 500Mohm or 25Mohm × μ F					
Resistance Tan δ : 0.075 max Max. operating temperature IR : 1,000Mohm or 50Mohm × μF 1000+48/-0hrs Whichever is smaller 0.000 + 48/-0hrs 0.000 + 48/-0hrs		Whichever is smaller					
Resistance Tan δ : 0.075 max Max. operating temperature IR : 1,000Mohm or 50Mohm × μF 1000+48/-0hrs Whichever is smaller 1000+48/-0hrs	High Temperature	Capacitance change : within ±12.5%	With 200% of the rated voltage				
Whichever is smaller		Tan δ : 0.075 max	-				
		IR : 1,000Mohm or 50Mohm × μF	1000+48/-0hrs				
Temperature Capacitance change : within ±7.5% 1 cycle condition		Whichever is smaller					
	Temperature	Capacitance change : within ±7.5%	1 cycle condition				
CyclingTan δ , IR : initial spec.Min. operating temperature \rightarrow 25°C	-	Tan δ, IR : initial spec.	-				
\rightarrow Max. operating temperature \rightarrow 25°C	-		\rightarrow Max. operating temperature \rightarrow 25°C				
5 cycle test			5 cycle test				

X The reliability test condition can be replaced by the corresponding accelerated test condition.

D. Recommended Soldering method :

Reflow (Reflow Peak Temperature : 260+0/-5°C, 10sec. Max)

Product specifications included in the specifications are effective as of March 1, 2013. Please be advised that they are standard product specifications for reference only. We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications,

please contact our sales personnel or application engineers.

- Disclaimer & Limitation of Use and Application -

The products listed in this Specification sheet are **NOT** designed and manufactured for any use and applications set forth below.

Please note that any misuse of the products deviating from products specifications or information provided in this Spec sheet may cause serious property damages or personal injury. We will **NOT** be liable for any damages resulting from any misuse of the products, specifically including using the products for high reliability applications as listed below.

If you have any questions regarding this 'Limitation of Use and Application', you should first contact our sales personnel or application engineers.

- Aerospace/Aviation equipment
- ② Automotive or Transportation equipment (vehicles, trains, ships, etc)
- 3 Medical equipment
- *④ Military equipment*
- *5* Disaster prevention/crime prevention equipment
- *ⓐ* Any other applications with the same as or similar complexity or reliability to the applications set forth above.